

Verbatim BVOH filament 1.75 mm - White

- **Product Number:** 55901

Product Specifications

Diameter accuracy:	1.75 mm \pm 0.07 mm
Extrusion temperature:	200°C - 220 °C
Material Net Weight:	0.5 kg
Filament Length:	182 m
Melt temperature:	176 °C
Melt Flow Rate @ 230 °C, 21.1N:	7.5 g/(10 minutes)
Density:	1.14 g/cm ³
Viscat softening temperature:	92 °C
Glass transition temperature:	68 °C
Flexural Strength:	71 MPa
Flexural Modulus:	2900 MPa
Tensile Strength:	45 MPa
Tensile Elasticity:	9.0%

Product Information

- Butenediol Vinyl Alcohol Co-polymer (BVOH) for material extrusion
- Water dissolvable support material for dual extruder printers
- Waste can be disposed with household effluent*
- Excellent layer-forming, emulsifying, adhesive
- Best in combination with Verbatim ABS, PLA, and PET material
- Light- and UV-sensitive
- High solubility
- Main applications: Support material for filaments, printing projects with overhangs or complex objects